

Quality

MTNTA-PU

| | |
|---------------|--|
| Fabric Weight | 79gsm +/- 5% |
| Composition | 70f24 x 70f24 (47 x 31.5/cm) 70D Nylon Taffeta |
| Finish | Dyed & PU Coated |
| Useable Width | 150cm |
| Application | Rainwear Lining |

Physical Properties

| | Warp | Weft |
|---|-------|-------|
| Tensile Strength (BS EN ISO 13934-1:2013) | 300 N | 300 N |
| Tear Strength (BS EN ISO 4674-1:2016) | 25 N | 25 N |

| | As Received | After 5 Washes |
|---|-------------|----------------|
| Abrasion Resistance (BS EN ISO 12947-2:2016) | NA | NA |
| Dimensional Stability (BS EN ISO 6330) | <3% | <3% |
| Spray Rating (BS EN ISO 4920:2012) | NA | NA |
| Water Vapour Resistance RET (BS EN ISO 11092) | NA | NA |
| Resistance to Water Penetration (BS EN ISO 20811) | 1000mm | NA |
| Colour Fastness | | |
| Light Fastness (BS EN ISO 105-E16:2006) | >4 | NA |
| Colour Fastness to Water (BS EN ISO 105-E01:2013) | >4 | NA |
| Perspiration Fastness Acid/Alkaline (BS EN ISO 105-E04) | >4 | NA |
| Wash Fastness (BS EN ISO 105-C10:2006) 40 Degrees | >4 | NA |
| Rub Fastness Wet/Dry (BS EN ISO 105-X12:1995) | >4 | NA |

The information contained in this product datasheet is based on results obtained from the sample assessed, following the method provided. The values are a guide for purchasers of the fabric to evaluate and determine its suitability for their product's intended end use.